

The rechargeable batteries are lead-lead dioxide systems. The dilute sulfuric acid electrolyte is absorbed by separators and plates and thus immobilized. Should the battery be accidentally overcharged producing hydrogen and oxygen, special one-way valves allow the gases to escape thus avoiding excessive pressure build-up. Otherwise, the battery is completely sealed and is, therefore, maintenance-free, leak proof and usable in any position.

**Battery Construction**


Component	Positive plate	Negative plate	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Copper	Fiberglass	Sulfuric acid

**General Features**

- Absorbent Glass Mat (AGM) technology for efficient gas recombination of up to 99% and freedom from electrolyte maintenance or water adding.
- Not restricted for air transport-complies with IATA/ICAO Special Provision A67.
- UL-recognized component.
- Can be mounted in any orientation.
- Computer designed lead, calcium tin alloy grid for high power density.
- Long service life, float or cyclic applications.
- Maintenance-free operation.
- Low self discharge.

**Dimensions and Weight**

Length(mm / inch).....151 / 5.94  
 Width(mm / inch).....65 / 2.56  
 Height(mm / inch).....94 / 3.70  
 Total Height(mm / inch).....100 / 3.94  
 Approx. Weight(Kg / lbs).....2.43 / 5.36



terminal  
F1 (0.187)

**Performance Characteristics**

Nominal Voltage .....12V  
 Number of cell .....6  
 Design Life .....3-5 years  
 Nominal Capacity 77°F(25°C)  
     20 hour rate (0.35A, 10.5V).....7Ah  
     10 hour rate (0.68A, 10.5V).....6.8Ah  
     5 hour rate (1.13A, 10.5V).....5.65Ah  
     1 hour rate (4.56A, 9.6V).....4.56Ah  
 Internal Resistance  
     Fully Charged battery 77°F(25°C).....28mOhms  
 Self-Discharge  
     3% of capacity declined per month at 20°C(average)  
 Operating Temperature Range  
     Discharge .....-20~60°C  
     Charge .....-10~60°C  
     Storage .....-20~60°C  
 Max. Discharge Current 77°F(25°C) .....105A(5s)  
 Short Circuit Current .....350A  
 Charge Methods: Constant Voltage Charge 77°F(25°C)  
     Cycle use .....14.5-14.9V  
     Maximum charging current .....2.8A  
     Temperature compensation.....-30mV/°C  
     Standby use .....13.6-13.8V  
     Temperature compensation.....-20mV/°C

**Discharge Constant Current (Amperes at 77°F25°C)**

End Point Volts/Cell	5min	10min	15min	30min	1h	3h	5h	10h	20h
1.60V	29.1	18.4	14.8	8.30	4.56	1.84	1.26	0.70	0.363
1.65V	27.5	17.5	14.2	7.90	4.40	1.80	1.22	0.69	0.359
1.70V	26.0	16.7	13.6	7.62	4.22	1.74	1.17	0.69	0.355
1.75V	24.4	15.7	13.0	7.24	4.04	1.68	1.13	0.68	0.350
1.80V	22.8	14.8	12.4	7.03	3.84	1.63	1.08	0.66	0.344

**Discharge Constant Power (Watts at 77°F25°C)**

End Point Volts/Cell	5min	10min	15min	30min	45min	1h	2h	3h	5h
1.60V	52.0	35.1	27.5	15.2	11.50	8.97	5.06	3.59	2.33
1.65V	49.4	33.3	26.5	14.6	11.00	8.59	4.94	3.50	2.29
1.70V	46.9	31.6	25.4	14.0	10.50	8.23	4.80	3.40	2.25
1.75V	44.5	29.8	24.3	13.4	10.10	7.99	4.65	3.30	2.21
1.80V	41.6	28.0	23.3	12.9	9.75	7.62	4.50	3.19	2.15

